

## CERTIFICATE OF CONFORMITY

### Test Pieces, 2.5mm Stainless Steel

Product Code	Product Detail
P8982-25	Metal Detectable Test Wand 2.5mm Stainless Steel

### Contaminant

Diameter	2.5mm
Material	Stainless Steel / AISI 316-L JIS SUS
Grade	100
Standard of Manufacture	ISO 3290 International
Density	8.0272 kg/ltr = 8.0272 g/cm3
Heat No.	FN180409AS05
Batch Number	1808065

Materials supplied from ISO 9001:2015 / Din Standard Quality Assured Suppliers.

### Chemical and Test Data of Contaminant

Carbon WT	C	0.220	Chrome %	Cr	16.380
Silicon	Si	0.366	Nickel %	Ni	10.090
Manganese %	Mn	0.930	Molibdeno %	Mo	2.010
Phosphorus %	P	0.038	Hardness	HRc	2.010
Sulphur %	Si	0.002			

## Manufacture of Test Piece Declaration

We hereby declare that our Test Pieces are manufactured from either the following materials and confirm:

- **Cast Acrylic – Sheets** are in conformity with requirements of EU regulation 1935/2004/EU on materials and articles intended to come in to contact with food. The used monomers and other raw materials meet the requirements of EU regulation No 10/2011
- **PTFE Grade 400 – Sheets** supplied are tested in accordance to FDA 177.1550
- **ACETAL COPOLYMER – CC34031 GREY FDA / CG34096 BLUE FDA / CS33273 RED FDA / CL33402E YELLOW FDA / CJ34045 GREEN FDA**
- **The Colour concentrate** meets the requirements for repeated Food Contact according to FDA 21 CFR 178.3297
- **ACETAL RESIN – Rods** are in conformity with Directive 2002/72/EC and FDA Regulation 21 CFR 177.2470
- **SEMI RIGID HOSING – Are** in conformity with Directive 1935/2004/EU and FDA Regulation 21 CFR 177.1500
- **POLYPROPYLENE – All monomers and additives** are in conformity with Directive 10/2011/EC and FDA 177.1520

## Test Piece Life Span

- The contaminant or sphere is secured in a Medium or Housing so has an indefinite life span. Life span of the contaminant or sphere all depends on the housing of the test piece
- Test Pieces life expectancy depends on a great extent of the use it receives. Furthermore, customers often replace Test Pieces long before they become worn out due to changes in mishandling and damage to the Test piece.
- If a Test piece becomes chipped, broken or unreadable we recommend new test pieces.

*This document was prepared on behalf of Klipspringer Ltd and the information included is provided in good faith and to the best of our knowledge correct at the time of writing. Klipspringer Ltd offers the information within this document as a guide only, and it does not represent any guarantee of the prescribed products in the sense of legal guaranteed relations. Klipspringer Ltd accepts no liability resulting from this document. It is the responsibility of the end user to ensure the items purchased are suitable for the intended application.*

The date on the Certificate of Conformity relates to when the contaminants or spheres were purchased. This cannot be altered as it allows traceability for Audit purposes.

Supplier	Klipspringer Ltd
Address	Foxtail House, Foxtail Road, Ipswich, Suffolk, UK. IP3 9RX.
Telephone	+44 (0) 1473 461 800
Email	sales@klipspringer.com
Website	www.klipspringer.com

Sheena Britton  
Technical Compliance Manager  
Klipspringer



Date of Issue	25-04-25
Authorised by	S. Britton
Revision No.	001
Revised by	O. Tydeman